

EEZ PRODUCTS

HYDRAULIC OILS ISO 22-460

For More Info, Visit..

EEZProducts.com

*Foamy Cutting Fluid
Tuf Tap 2-15-T
Insted-A-Led*

*Micro Max
Cool Aid
Ultrafinish*

*Saftee Cut
Thread Cut Cutting Oils*

*White Kut Soluble Oils
Clean Wheel Coolants
Cost Cut Synthetic Coolants*

*Saw Cut #683
Delta #900 Coolants
XP Rust Preventives*

*Saver Chain & Cable Fluid
Way Oil
Hydraulic Oil*

*Spindle Oil
Compressor Oil
Grease*

*Synthetic Gear Oil
Synthetic Hydraulic Oil*

Made In U.S.A.

**Mullen Circle Brand, Inc.
EEZ Products Division**

3514 West Touhy Ave
Skokie, IL 60076
847/676-1880

Fax: 847/676-3748

Solutions@MullenOil.com



Premium Antiwear Lubricants For Modern Hydraulics

EEZ Products Antiwear Hydraulic Oils are premium grade lubricants designed to meet the needs of modern hydraulic equipment. **Antiwear Hydraulic Oils** are blended from virgin base oils and premium additive technology. These products exhibit exceptional resistance to thermal degradation, excellent demulsibility and are inert to copper alloys.

Antiwear Hydraulic Oils meet or exceed the following:

Denison HF-0	DIN 51524-2 (HM)	JCMAS P041 HK
Denison HF-1	DIN 51524-3 (HV)	ANSI/AGMA 9005-E02-RO
Denison HF-2	ISO 11158 (HM, HV)	GM LS-2
Eaton M-2950-S	ASTM D2168 (HM, HV)	AIST 126, 127
Eaton I-286-S3	SAE MS 1004 (HM, HV)	SEB 181222
MAG P68, P69, P70	Bosch Rexroth RE 90220	

More ==>

...Providing Solutions To Industry Since 1912...

Mullen Circle Brand, Inc.

EEZ PRODUCTS DIVISION

3514 W. Touhy Avenue
Skokie, IL 60076

Phone 847/676-1880

Fax 847/676-3748

Solutions@MullenOil.com

EEZ PRODUCTS ANTIWEAR HYDRAULIC OILS

	<u>#22</u>	<u>#32</u>	<u>#46</u>	<u>#68</u>	<u>#100</u>	<u>#150</u>	<u>#220</u>	<u>#320</u>	<u>#460</u>
ISO Grade	22	32	46	68	100	150	220	320	460
SAE Grade	5	10	20	20	30	40	50	—	—
Viscosity, SUS @ 100 F	110	160	240	353	520	750	1150	1673	2404
Flash Point, F	390	400	400	400	400	400	400	400	460
Pounds/Gallon	7.1	7.1	7.29	7.43	7.56	7.65	7.67	7.68	7.69
Oxidation Stability, ASTM D-943									
1000 Hours, Neutralization Number									0.3
Sludge									56 mg
Copper									100.33 mg
Thermal Stability, 135 C									
Viscosity Change, %									1.2
Neutralization Number Change, %									133
Sludge, mg/100 ml									2.3
Steel Rod	Visual								1
	Deposit, mg								0.3
Copper Rod	Visual								2
	Deposit, mg								0.1
Demulsibility, ASTM D-1401									
Oil/Water/Emulsion (Minutes)									40/40/0 (5)
Steel Corrosion Test, ASTM D-665									
Distilled Water									No Rust
Synthetic Seawater									No Rust
Foam Tests, ASTM D-982, Seq I, II, III									
Foam, ml, 10 Minutes									None
Copper Corrosion, ASTM D-130									
									1B
Wear Test, Four Ball									
40 kg, 1800 rpm, 1 Hour, 55C									.62 mm

***** Cross Reference *****

ISO 32 Hydraulic Oil = Mobil DTE 24

ISO 46 Hydraulic Oil = Mobil DTE 25

ISO 68 Hydraulic Oil = Mobil DTE 26

...Providing Solutions To Industry Since 1912...

Cutting Fluids * Industrial Lubricants * Greases * Cleaners

The Information Given Herein Is Believed To Be Reliable, But No Guarantee Is Made Nor Liability Assumed.